



PRODUCT DATASHEET

BI-METAL COMPOSITE PANEL FASTENER

Product Details

Designed for:	<i>Fixing cladding/roofing applications to hot/cold purlins/rails. Fastening liner panels and general components to steel. Fastening brick-tie channel through Insulation to SFS.</i>
Head style:	<i>Hexagonal</i>
Drive bit:	<i>5/16" hexagonal</i>
High Thread form:	<i>Coarse thread</i>
Primary Thread form:	<i>Coarse thread (Tek 3) / Fine thread (Tek 5)</i>
Shank material:	<i>AISI A304</i>
Material grade:	<i>AISI A304</i>
Recommended drill speed:	<i>1500 – 2500RPM</i>

Bi-Metal Composite Panel Fastener Range

Product Code	Nominal Dimensions	Washer Diameter	Insulation Thickness Range
Products for use in Light Gauge Applications (1.2mm to 4.0mm mild steel)			
BMTSBWHT5.5-80-3	5.5 x 80mm	16mm	20 – 60mm
BMTSBWHT5.5-105-3	5.5 x 105mm	16mm	50—90mm
BMTSBWHT5.5-115-3	5.5 x 115mm	16mm	40—95mm
BMTSBWHT5.5-135-3	5.5 x 135mm	16mm	60—120mm
BMTSBWHT5.5-150-3	5.5 x 150mm	16mm	75—130mm
BMTSBWHT5.5-165-3	5.5 x 165mm	16mm	90 – 145mm
BMTSBWHT16-5.5-185-3	5.5 x 185mm	16mm	110 – 165mm
BMTSBWHT5.5-185-3	5.5 x 185mm	19mm	110 – 165mm
BMTSBWHT5.5-235-3	5.5 x 235mm	19mm	155 – 220mm
BMTSBWHT5.5-275-3	5.5 x 275mm	19mm	195– 255mm
Products for use in Heavy Gauge Applications (4.0mm to 12.5mm mild steel)			
BMTSBWHT5.5-105-5	5.5 x 105mm	16mm	25 – 85mm
BMTSBWHT5.5-125-5	5.5 x 125mm	16mm	40 – 105mm
BMTSBWHT5.5-150-5	5.5 x 150mm	19mm	50 – 130mm
BMTSBWHT5.5-185-5	5.5 x 185mm	19mm	85 – 165mm
BMTSBWHT5.5-245-5	5.5 x 245mm	19mm	135 – 215mm

NOTE: The results expressed in the datasheet are taken as mean loads from a range of empirical tests and are ultimate unfactored loads. Each specifier or end user should make his/ her own decision on what safety factors to use relevant to their design application (such as BS 5950, EN 1991, etc).

Errors and Omissions Excepted.

Copyright © 2018 Evolution Fasteners (UK) Ltd. All rights reserved.



Technical Data

Tek 3 range – unfactored pull out values							
Diameter	Drill point	Steel Thickness					
		1.2mm	1.6mm	2.0mm	2.5mm	3.0mm	4.0mm
5.5mm	Tek 3	1.7kN	2.1kN	2.5kN	3.3kN	4.1kN	5.4kN

Tek 5 range – unfactored pull out values							
Diameter	Drill point	Steel Thickness					
		4mm	5mm	6mm	8mm	10mm	12.5mm
5.5mm	Tek 5	6.4kN	7.7kN	10.1kN	11.4kN	12.3kN	12.8kN

Hardness Rating (Vickers scale)		
Diameter	Surface Hardness	Core Hardness
5.5mm	465.6 HV0.3	323.7 HV0.3

Pullover Performance		
Diameter	In 0.6mm steel	In 1.2mm steel
5.5mm	2.4kN	8.1kN

Ultimate Mechanical Performance		
Diameter	Tensile Strength	Shear Strength
5.5mm	13.3kN	9.9kN